

Product Data Sheet

Product: Bovine Bone Gelatine (type B limed bone gelatins)

Applications: For manufacturing of soft (softgels) and hard gelatin capsules. We

can customise gelatins are per customer requirements.

Shelf-life: 5 years

TESTS	SPECIFICATIONS
PHYSICAL AND CHEMICALS TESTS	
Gel strength	Customisable
(6.67% at 10°C for 16-18 hours)	(from 150 g to 270 g)
Moisture	Max. 13%
pH (10% at 30°C)	5.5 – 6.2
Viscosity	Customisable
(6.67% at 60°C)	(from 30 – 50 mPs)
Appearance	Faint yellow powder
Odour	Free from disagreeable odour
Solubility	Soluble in hot water
Transmittance % (510 nm)	Min. 75%
Ash	Max. 2%
Sulfur Dioxide SO2 (ppm)	Max. 40
Iron (ppm)	Max. 10 ppm
Arsenic (ppm)	Max. 0.8 ppm
Cadmium (ppm)	Max. 0.5 ppm
Lead (ppm)	Max. 5 ppm
Mercury (ppm)	Max. 0.15 ppm
MICROBIAL TESTS	
Total Bacterial Count	< 500 cfu/gm
Escherichia Coli /10 g	Absent
Salmonella sp /10 g	Absent
Yeast and molds (MAHS)	< 100 cfu/gm